

EN AW-8130

ASTM 8130 · 8xxx · Al-Fe (low creep)

DESIGNATIONS

EN AW EN AW-8130	ASTM / US 8130	DIAMETERS 9.0; 9.5 mm	Σ , MPA 60-130
----------------------------	--------------------------	---------------------------------	---------------------------------

APPLICATIONS

High-conductivity building cables, medium-voltage power cables.

ADVANTAGES

- High conductivity for the 8xxx series (up to 61.5% IACS)
- Good mechanical properties
- Stable performance in energy systems

TEMPER STATES

TEMPER	DIAMETER, MM	TENSILE STRENGTH, MPA	ELONGATION, MIN, %	RESISTIVITY, MAX, $\Omega \cdot \text{MM}^2/\text{M}$	CONDUCTIVITY, MIN, % IACS
F	9.0; 9.5	85-130	10	0.02855	61.2
O	9.5	60-110	25	0.02850	61.4

CHEMICAL COMPOSITION, %

DESIGNATIONS	MIN %	MAX %
Si	—	0.150
Fe	0.400	1.000
Cu	0.050	0.150
Mn	—	0.010
Mg	—	0.010
Zn	—	0.100
Al (Al, min)		balance
Other impurities — each		$\leq 0.03\%$
Other impurities — total		$\leq 0.10\%$

Alusilk

PART OF ITS GROUP

Coiled Aluminium · Connected Future

HEADQUARTERS

Dubai Silicon Oasis, Dubai, UAE

+971 50 153 0202

info@alusilk.ae

UZBEKISTAN BRANCH

7 Abdulla Qodiriy St · Yunusobod district ·

Tashkent

+998 97 341 2222

alusilk.uz · alusilk.ae