

EN AW-6201

ASTM 6201 · 6xxx · Al-Mg-Si (issiqlik bilan mustahkamlanadigan)

BELGILANISHLAR

EN AW EN AW-6201	ASTM / US 6201	DIAMETRLAR 9.5 mm	Σ , MPA 160-330
----------------------------	--------------------------	-----------------------------	----------------------------------

QO'LLANISH SOHASI

Yuqori mexanik chidamlilikdagi havo liniyalari uchun faqat alyuminiy qotishmasi (AAAC) o'tkazgichlari.

AFZALLIKLAR

- 6xxx seriyasining maksimal mustahkamligi (330 MPa gacha)
- Yuqori charchoq chidamliligi
- T81 holati — mustahkamlik va o'tkazuvchanlik balansi
- IEC va ASTM ga muvofiq

YETKAZIB BERISH HOLATLARI

HOLAT	DIAMETR, MM	MUSTAHKAMLIK CHEGARASI, MPA	CHO'ZILISH, MIN, %	SOLISHTIRMA QARSHILIK, MAKS, $\Omega \cdot \text{MM}^2/\text{M}$	O'TKAZUVCHANLIK, MIN, % IACS
T1	9.5	160-205	17	0.03600	47.8
T4	9.5	205-330	8	0.03600	47.8
T81	9.5	315-330	3	0.03700	46.5

KIMYOVIY TARKIB, %

BELGILANISHLAR	MIN %	MAX %
Si	0.500	0.900
Fe	—	0.500
Cu	—	0.100
Mn	—	0.030
Mg	0.600	0.900
Cr	—	0.030
Zn	—	0.100
B	—	0.060

BELGILANISHLAR	MIN %	MAX %
Al (Al, min)		qoldiq
Boshqa aralashmalar — har biri		≤ 0.03%
Boshqa aralashmalar — jami		≤ 0.10%

Alusilk
PART OF ITS GROUP
Coiled Aluminium · Connected Future

BOSH OFIS
Dubai Silicon Oasis, Dubai, UAE
+971 50 153 0202
info@alusilk.ae

O'ZBEKISTONDAGI FILIAL
Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani
· Toshkent
+998 97 341 2222
alusilk.uz · alusilk.ae