

# EN AW-8176

ASTM 8176 · 8xxx · Al-Fe (past oqim)

## BELGILANISHLAR

EN AW <b>EN AW-8176</b>	ASTM / US <b>8176</b>	DIAMETRLAR <b>9.0; 9.5 mm</b>	Σ, MPA <b>60-140</b>
----------------------------	--------------------------	----------------------------------	-------------------------

## QO'LLANISH SOHASI

Turar joy va tijoriy binolar uchun qurilish kabellari va o'rnatish simlari.

## AFZALLIKLAR

- Kontaktlarda past oqim
- Egiluvchanlik — o'rnatish qulayligi
- UL va IEC talablariga muvofiq
- Misga iqtisodiy samarali muqobil

## YETKAZIB BERISH HOLATLARI

HOLAT	DIAMETR, MM	MUSTAHKAMLIK CHEGARASI, MPA	CHO'ZILISH, MIN, %	SOLISHTIRMA QARSHILIK, MAKS, Ω·MM <sup>2</sup> /M	O'TKAZUVCHANLIK, MIN, % IACS
<b>F</b>	9.0; 9.5	115-140	10	0.02855	60.4
<b>O</b>	9.5	60-110	30	0.02860	61

## KIMYOVIY TARKIB, %

BELGILANISHLAR	MIN %	MAX %
<b>Si</b>	0.030	0.150
<b>Fe</b>	0.400	1.000
<b>Cu</b>	—	0.040
<b>Mn</b>	—	0.030
<b>Zn</b>	—	0.100
<b>Ga</b>	—	0.030
<b>V</b>	—	0.020
<b>Al (Al, min)</b>		<b>qoldiq</b>
Boshqa aralashmalar — har biri		≤ 0.05%

BELGILANISHLAR	MIN %	MAX %
Boshqa aralashmalar — jami		≤ 0.15%

**Alusilk**  
PART OF ITS GROUP  
Coiled Aluminium · Connected Future

**BOSH OFIS**  
Dubai Silicon Oasis, Dubai, UAE  
+971 50 153 0202  
info@alusilk.ae

**O'ZBEKISTONDAGI FILIAL**  
Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani  
· Toshkent  
+998 97 341 2222  
alusilk.uz · alusilk.ae