

EN AW-8177

ASTM 8177 · 8xxx · Al-Fe (past oqim)

BELGILANISHLAR

| | | | |
|----------------------------|--------------------------|-----------------------------|-------------------------|
| EN AW EN AW-8177 | ASTM / US 8177 | DIAMETRLAR 9.5 mm | Σ, MPA 60-130 |
|----------------------------|--------------------------|-----------------------------|-------------------------|

QO'LLANISH SOHASI

Turar joy va tijoriy qurilishi uchun qurilish kabellari.

AFZALLIKLAR

- Nazorat ostidagi aralashmalar
- Barqaror mexanik xossalar
- Standartlashtirilgan qurilish tizimlari uchun mos

YETKAZIB BERISH HOLATLARI

| HOLAT | DIAMETR, MM | MUSTAHKAMLIK CHEGARASI, MPA | CHO'ZILISH, MIN, % | SOLISHTIRMA QARSHILIK, MAKS, Ω·MM ² /M | O'TKAZUVCHANLIK, MIN, % IACS |
|----------|-------------|-----------------------------------|-----------------------|--|---------------------------------|
| F | 9.5 | 90-130 | 10 | 0.02860 | 61 |
| O | 9.5 | 60-110 | 25 | 0.02850 | 61.2 |

KIMYOVIY TARKIB, %

| BELGILANISHLAR | MIN % | MAX % |
|--------------------------------|---------------|-------|
| Si | — | 0.100 |
| Fe | 0.250 | 0.450 |
| Cu | — | 0.040 |
| Mn | — | 0.010 |
| Mg | — | 0.010 |
| Zn | — | 0.050 |
| B | — | 0.040 |
| Al (Al, min) | qoldiq | |
| Boshqa aralashmalar — har biri | ≤ 0.03% | |
| Boshqa aralashmalar — jami | ≤ 0.10% | |

Alusilk

PART OF ITS GROUP

Coiled Aluminium · Connected Future

BOSH OFIS

Dubai Silicon Oasis, Dubai, UAE

+971 50 153 0202

info@alusilk.ae

O'ZBEKISTONDAGI FILIAL

Abdulla Qodiriy ko'chasi, 7 · Yunusobod tumani

· Toshkent

+998 97 341 2222

alusilk.uz · alusilk.ae